

# MDF AE GREEN

DIVISIONE PANNELLI  
BOARD DIVISIONPer usi generali in ambiente umido.  
*General purpose, humid conditions.*

	Metodo di prova <i>Test method</i>	Unità di misura <i>Unit</i>	Campo di spessore nominale (mm) <i>Range of nominal thicknesses (mm)</i>				
			6 - 9 min. <sup>2</sup>	> 9 - 12 min. <sup>2</sup>	> 12 - 19 min. <sup>2</sup>	> 19 - 30 min. <sup>2</sup>	> 30 - 45 min. <sup>2</sup>
<b>Caratteristiche meccaniche</b>							
Res. Allo strappo / <i>Internal bond</i>	EN 319	N/mm <sup>2</sup>	0,80	0,80	0,75	0,75	0,70
C.R.F. / <i>Bending strength</i>	EN 310	N/mm <sup>2</sup>	27	26	24	22	17
MOE / <i>Modulus of elasticity</i>	EN 310	N/mm <sup>2</sup>	2700	2500	2400	2300	2200
Opz. 1 - Rig. in spessore dopo test ciclico1 / <i>Cyclic test Opt.1 Swelling1</i>	EN 321	N/mm <sup>2</sup>	19	16	15	15	15
Opz. 1 - Res. Strappo dopo test ciclico / <i>Cyclic test Opt.1 internal bond</i>	EN 321	N/mm <sup>2</sup>	0,30	0,25	0,20	0,15	0,10
Tenuta delle viti / <i>Screwholding</i>			Non applicabile a spessori inferiori a 15 mm	Not applicable for thickness less than 15 mm			
Faccia / <i>Face</i>	EN 320	N			1000	1000	1000
Bordo / <i>Edge</i>	EN 320	N			800	750	700
Strappo superfic. / <i>Surface soundness</i>	EN 311	N/mm <sup>2</sup>	1,2	1,2	1,2	1,2	1,2

<b>Caratteristiche fisiche</b>							
Ass. Sup. (toluolo) / <i>Surface absorption</i>	EN 382-1	mm	150	150	150	150	150
Rigonf. 24 h (max) / <i>Thickness swelling 24h</i>	EN 317	%	12	10	8	7	7
Densità <sup>3</sup> / <i>Density</i>	EN 323	Kg/m <sup>3</sup>	820 ± 5%	780 ± 5%	760 ± 5%	730 ± 5%	720 ± 5%
Umidità / <i>Moisture content</i>	EN 322	%			5 - 9		
Content. in silice / <i>Sand content</i>	ISO 3340	%			≤ 0,05		

<b>Caratteristiche geometriche</b>							
Squadro / <i>Squareness</i>	EN 324-2	mm/m			± 2,0		
Toll. di spessore <sup>4</sup> / <i>Thickness tolerance</i>	EN 324-1	mm			± 0,2		
Toll. lungh. e largh. / <i>Lenght and width tol.</i>	EN 324-1	mm/m		± 2,0 mm/m, massimo assoluto ± 5,0 mm / ± 2,0 mm/m, absolute maximum ± 5,0 mm			

<b>Formaldeide<sup>5</sup> / Formaldehyde</b>							
Classe E1 / <i>Class E1</i>	EN12460-5	mg/100g			≤ 8		

1-CE Fantoni S.p.a. EN 13986 – MDF-E1, classe di reazione al fuoco D-S2, d0, (spessore ≥ 9 mm), classe E (spessore ≥ 3 mm &lt; 9 mm).

2-I valori indicano i requisiti prestazionali minimi (corrispondono a valori massimi nel caso del rigonfiamento e a valori minimi negli altri casi) e sono uguali o migliorativi rispetto alla norma EN 622-5.

3-Da intendersi come dato medio riferito al pannello grezzo intero; per i pannelli nobilitati vi è un incremento dipendente dal decorativo.

4-Per i Pannelli nobilitati vi è un incremento di spessore dipendente dal decorativo.

5-Il pannello (articolo) ha un contenuto di formaldeide determinato con il metodo del perforatore, riferito ad una umidità del 6,5% (classe di formaldeide E1), inferiore allo 0,1% p/p.

Non sussiste pertanto per il produttore l'obbligo di informazione ai sensi del Art. 33 comma 1 Regolamento EU1907/2006 REACH.

"Art. 33 comma 1. Il fornitore di un articolo contenente una sostanza che è presente nell' allegato XIV in concentrazioni superiori allo 0,1% in peso /peso fornisce al destinatario dell'articolo informazioni, in possesso del fornitore, sufficienti a consentire la sicurezza d'uso dell'articolo e comprendenti quanto meno, il nome della sostanza."

Per informazioni in merito alla riclassificazione della formaldeide Carc. 1B, si consiglia di far riferimento al documento Federlegno "Formaldeide – Riclassificazione della sostanza come cancerogeno 1B operativa dal 1° gennaio 2016".

1- CE Fantoni S.p.a. EN 13986 – MDF-E1, fire rating D-S2, d0, (thickness ≥ 9 mm), class E (thickness ≥ 3 mm &lt; 9 mm).

2- These values indicate the minimum performance required (maximum values for swelling and minimum values for all other parameters) and are equal to or better than standard EN 622-5.

3- To be read as an average figure with reference to the whole untreated panel; for faced panels, there will be an increase, which will depend on the decorative paper used.

4- For faced panels, the decorative paper used will determine an increase in thickness.

5- The formaldehyde content of the panel (item), determined by the perforation method and based on a humidity level of 6.5 % (formaldehyde class E1), is below 0.1% w/w.

For this reason the producer is not obliged to provide information as per article 33 paragraph 1 of EU 1907/2006 REACH regulations.

"Art. 33 paragraph 1. Any supplier of an article containing a substance meeting the criteria in Article 57 and identified in accordance with Article 59 (1) in a concentration above 0,1 % weight by weight (w/w) shall provide the recipient of the article with sufficient information, available to the supplier, to allow safe use of the article including, as a minimum, the name of that substance."

For information regarding the reclassification of formaldehyde Carc. 1B, we recommend referring to the Federlegno document "Formaldehyde – Reclassification of the substance as a category 1B carcinogen as of 1st January 2016".

